CARBONCURE™

CarbonCure™ Concrete Admixture

ASTM C 494 Type S - Cement Hydration Enhancing Admixture

Product Description

CarbonCure Technologies offers a technology to implement carbon dioxide (CO_2) utilization in the concrete industry. The CO_2 (hereafter, CarbonCure concrete admixture) is added to concrete during mixing and acts as a cement hydration enhancing admixture based on the CO_2 mineralization process. CarbonCure concrete admixture permits a reduction in the total cementitious materials content of a given concrete mixture while maintaining fresh properties, strength and durability performance, thus reducing the carbon footprint of concrete. CarbonCure concrete admixture meets ASTM C494 requirements for Type S, Specific Performance Admixtures.

Uses

CarbonCure concrete admixture is used to produce concrete mixtures with a reduced carbon footprint. Concrete shall be designed in accordance with Standard Recommended Practice for Selecting Proportions for Concrete, ACI 211. CarbonCure concrete admixture is recommended for use in both ready-mixed and precast concrete.

Benefits

The addition of CarbonCure concrete admixture to concrete mixtures can realize benefits, including:

- Concrete produced with a reduced carbon footprint
- Ability to improve both early- and late-age compressive strengths
- Optimized and better performing concrete mixtures

CO_2 Mineralization Technology

When the CarbonCure concrete admixture is injected in the fresh concrete, it chemically converts into a nano-scale calcium carbonate mineral (i.e., the CO_2 is mineralized in-situ) and becomes permanently captured in the concrete. The formation of this mineral has been demonstrated to improve the cement hydration efficiency, which is the ratio of compressive strength to the amount of cement in concrete.

Guidelines for Use

Dosage Rates: CarbonCure has a recommended dosage rate of 0.1 - 10.0 fl oz/cwt (6.25-625 g/100 kg) of cement (as distinct from total cementitious) for most applications. Dosages outside this range may be used if local testing shows acceptable performance. Pretesting is required to determine the appropriate dosage rate for desired performance. The optimum dosage rate may be influenced by other concrete mixture components, cement types, ambient temperature, mineral additives, quality and gradations of aggregates, slump of concrete, mixing equipment, job conditions, and desired performance characteristics.

Mixing: The optimum performance of the CarbonCure concrete admixture is generally obtained with a delayed dosage following the cement-water contact in the mixer. A mixing cycle of at least 30 seconds after the complete CO_2 injection in the mixture is strongly recommended.

Packaging and Handling

CarbonCure concrete admixture is available in bulk and delivered by tanker truck to an on-site pressurized storage tank for dispensing by means of the CO_2 metering equipment. CarbonCure concrete admixture must have a certified purity of 99% or above for use in this application – certification of purity compliance shall be made available upon request. CarbonCure concrete admixture safety and handling information can be found in the Carbon Dioxide safety data sheet CAS No: 124-38-9.

Dispensing Equipment

CarbonCure concrete admixture is dispensed from a storage tank of liquid CO 2 in communication with the dispensing control system. The tank and CO 2 are sourced from a local industrial gas supplier. The tank capacity is determined according to the usage and gas supplier recommendation. The dispensing control system is connected to the batching system and the CO 2 addition is fully integrated into the batch sequencing of materials that are added to the concrete mixture.

CarbonCure™ Concrete Admixture

ASTM C 494 Type S - Cement Hydration Enhancing Admixture

Related Documents

See MSDS for CO 2 as provided by the industrial gas supplier.

Note

Continuous testing by the concrete producer is strongly recommended. Since all cements and other concrete-making materials differ from source to source, and can vary over time, ongoing testing by the concrete producer is recommended for optimum CO_2 system performance, especially when changes are made to the materials or batch sequencing. Accurate concrete performance assessment requires adequate quality control practices. The CO_2 injection system performance is supported through following all recommended maintenance practices, procedures, and schedules.

The information provided herein is intended to be a guide developed upon data, practices and knowledge considered to be true and accurate. The information is offered for the user's consideration, investigation and verification, but results are not warranted to be obtained. Satisfactory results depend not only upon quality materials and many other factors beyond our control. Therefore, CARBONCURE MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, RESPECTING CARBONCURE TECHNOLOGY, CARBONCURE PRODUCTS AND CARBONCURE SERVICES AND CARBONCURE SHALL HAVE NO LIABILITY WITH RESPECT THERETO. User shall determine the suitability of the technology for the intended use and assume all risks and liability in connection therewith. The information is subject to change without notice. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right. CARBONCURE SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. CarbonCure reserves the right to make any changes according to technological progress or further developments. CARBONCURE and CO2CRETE are trademarks, which may be registered in the United States and/or other countries, of CarbonCure Technologies Inc.

© Copyright 2026 CarbonCure Technologies Inc. All rights reserved.